



SUBSTITUTE ABSTRACT OF THE DISCLOSURE

RECEIVED
AUG 26 2003
TC 1700

A graft copolymer composition obtained by mixing a graft copolymer (A) containing a rubbery polymer having a glass transition temperature of not higher than 0°C as a trunk polymer and containing a alkyl ester of methacrylic acid-base polymer as a graft component, and having a mean particle size of at least 0.15 μm , and a graft copolymer (B) having a means particle size of from 0.03 to 0.13 μm ; and a vinyl chloride-base resin composition containing the above described graft copolymer composition as an impact modifier, with excellent impact strength and suitable for use in the productions of pipes, window frames, joints, fences, doors, switch boxes, etc.